

TECHNICAL CHARACTERISTICS FLUIDISING CANVAS AET/4900/AET	
COMPOSITION	URDIMBRE : 100% POLYESTER (MULTIFILAMENT) 1000 Deniers WEFT: 100% POLYESTER (CUT FIBRE) Nm9 1/C
CONSTRUCTION	THREE LAYERS URDIMBRE 250 Threads /cm TRAMA 130 Threads /cm
THICKNESS	6,0 +- 0,5 mm
SPECIFIC WEIGHT	4900 +- 300 grs7m2
PERMEABILITY	2 +-0,5 m3/m2/min (300mm c.a.)
TENSILE STRENGTH	URDIMBRE 7400 N/cm (+-10%) TRAMA 5000 N/cm(+-10%)
ELONGATION AT BREAK	URDIMBRE 115%(+-15%) TRAMA 30% (+-15%)
MAXIMUM CONTINUOUS TEMPERATURE	150°C (200°C Spikes)